

In re Patent Application of:

YAO

Serial No. 10/736,859

Filed: 12/16/2003

IN THE CLAIMS:

Claims 1-18 (cancelled)

19. (cancelled)

20. (currently amended) ~~The method according to claim 19A~~
method of generating an electrical current in response to light
comprising the steps of:

(a) absorbing light by a light-absorption intrinsic semiconductor layer having a thickness t_i , a doping concentration below $5 \times 10^{14} \text{ cm}^{-3}$, and producing, in response to light absorbed by said light-absorption intrinsic semiconductor layer, electrical carriers that are transported therethrough;

(b) absorbing light by a first light absorption doped semiconductor layer doped with one of p- and n-conductivity type-determining impurities, having a thickness t_{d1} , and a first doping concentration dc_1 between 1×10^{17} and $2 \times 10^{18} \text{ cm}^{-3}$, said first light absorption doped semiconductor layer having a first surface thereof abutting a first surface of said light absorption intrinsic semiconductor layer, and producing, in response to light absorbed by said first light absorption doped semiconductor layer, electrical carriers that are transported therethrough, and wherein t_{d1}/t_i is greater than or equal to 0.17; and

(c) extracting electrical current comprised of said carriers produced by and transported through said light-absorption intrinsic semiconductor layer and said first light absorption doped semiconductor layer, by means of a first electrode electrically coupled to said first light absorption doped semiconductor layer, and a second electrode electrically coupled to said light absorption intrinsic semiconductor layer, wherein

step (b) further comprises absorbing light by a second light absorption doped semiconductor layer doped with the other of said

In re Patent Application of:

YAO

Serial No. 10/736,859

Filed: 12/16/2003

p- and n-conductivity type-determining impurities, having a thickness td_2 , and a second doping concentration dc_2 between $1e17$ and $2e18\text{ cm}^{-3}$, said second light absorption doped semiconductor layer having a first surface thereof abutting a second surface of said light absorption intrinsic semiconductor layer that is spaced apart from said first surface of said light absorption intrinsic semiconductor layer by material of said light absorption intrinsic semiconductor layer therebetween, and producing, in response to light absorbed by said second light absorption doped semiconductor layer, electrical carriers that are transported therethrough, and wherein $(td_1+td_2)/t_i$ is greater than or equal to 0.17, and

step (c) comprises extracting said electrical current, comprised of said carriers produced by and transported through said light-absorption intrinsic semiconductor layer and said first and second light absorption doped semiconductor layers, by means of said first electrode electrically coupled to said first light absorption doped semiconductor layer, and said second electrode electrically coupled to said second light absorption doped semiconductor layer.

21. (previously presented) The method according to claim 20, wherein said first light absorption doped semiconductor layer comprises a light absorption p-doped semiconductor layer and said second light absorption doped semiconductor layer comprises a light absorption n-doped semiconductor layer, and wherein

step (c) comprises extracting said electrical current by means of a p-doped anode electrode electrically coupled to a second surface of said light absorption p-doped semiconductor layer, and an n-doped cathode electrode electrically coupled to a second surface of said light absorption n-doped semiconductor layer.

22. (cancelled)

In re Patent Application of:

YAO

Serial No. **10/736,859**

Filed: **12/16/2003**

23. (previously presented) The method according to claim 20, wherein the total thickness $td1+td2+ti$ of said first and second light absorption semiconductor layers and said light absorption intrinsic semiconductor layer is greater than $v/(2f_{3-dB})$ by 20% or more, where v is the saturation drift velocity of either an electron or a hole, whichever is smaller, in said light absorption intrinsic semiconductor layer, and wherein f_{3-dB} is the frequency at which the amplitude of responsivity of said method is reduced to $1/\sqrt{2}$ of its DC low-frequency value.

24. - 26. (cancelled)

27. (previously presented) The method according to claim 20, wherein, for a 3-dB bandwidth frequency of 40GHz or higher, said first and second light absorption doped semiconductor layers and said light absorption intrinsic semiconductor layer are InGaAs lattice-matched to InP, and the total thickness ($td1+td2+ti$) of said first and second light absorption doped semiconductor layer and said light absorption intrinsic semiconductor layer is greater than 0.60 microns.

28. (previously presented) The method according to claim 20, wherein, for a 3-dB bandwidth frequency of 40GHz or higher, said first and second light absorption doped semiconductor layers and said light absorption intrinsic semiconductor layer are InGaAs lattice-matched to InP, and the total thickness ($td1+td2+ti$) of said first and second light absorption doped semiconductor layer and said light absorption intrinsic semiconductor layer is greater than 0.65 microns.

29. (previously presented) The method according to claim 20, wherein, for a 3-dB bandwidth frequency of 40GHz or higher, said

In re Patent Application of:

YAO

Serial No. **10/736,859**

Filed: **12/16/2003**

first and second light absorption doped semiconductor layers and said light absorption intrinsic semiconductor layer are InGaAs lattice-matched to InP, and the total thickness ($td1+td2+ti$) of said first and second light absorption doped semiconductor layer and said light absorption intrinsic semiconductor layer is greater than 0.70 microns.

30. - 40. (cancelled)